

December 20, 2016

Ad-n-Art
Attn: Ben Petersen, Vice President

Subject: Certification of Polymer Material

Mr. Petersen,

In response to certify the composition of the Ad-n-Art Pill Organizer bottles (see **Figures 1, 2, & 3**) manufactured from Eastman Tritan™ Copolyester, we are providing the infrared spectra and Differential Scanning Calorimetry (DSC) curves. The bottle lids were not analyzed, only the containers.

The IR spectra of Tritan™ Copolyester and the test samples provided were obtained using a Nicolet 6700 FTIR spectrometer with a silicon crystal attenuated total reflectance accessory. The spectra were normalized and baseline-corrected for comparison. The Ad-n-Art bottles spectra provided are consistent with the IR spectrum of a Tritan™ Copolyester reference (see **Figure 4, 5, & 6**).

The DSC curves provided are consistent with Tritan™ grade TX1001 (see **Figures 7, 8, & 9**). The DSC test method to measure the glass transition temperature used the following conditions: 2nd heating @ 20°C/min; in N₂, Instrument: DSC Q2000.

The analytical data concludes that the Ad-n-Art Pill Organizer bottles provided were manufactured from Eastman Tritan™ Copolyester.

There may be differences between these results provided by Eastman and those obtained from outside testing due to slightly different equipment and techniques; however, the relative difference between Tritan™ and other polymers should be comparable when measured on the same equipment, the same sampling technique, and the same analysis conditions.

This information embodied in this letter is strictly confidential and is supplied on the understanding that this information will be held in confidentiality and not disclosed to third parties without the prior written consent of Eastman Chemical Company.

Sincerely,



Brett N. Jones
Eastman Chemical Company
Durables and Medical, Applications Development
137 Regional Park Drive
Kingsport, TN 37660
Phone: 423-229-6415

**Figure 1 – Yellow
Test Sample**





**Figure 2 – Blue
Test Sample**



**Figure 3 – Pink
Test Sample**



Neither Eastman nor its marketing affiliates shall be responsible for the use of this information, or of any product, method or apparatus mentioned, and you must make your own determination of its suitability and completeness of your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability or fitness of any product; and nothing herein waives any of the Seller's conditions of sale.

Figure 4 – FTIR Spectra**Figure 5 – FTIR Spectra**

Neither Eastman nor its marketing affiliates shall be responsible for the use of this information, or of any product, method or apparatus mentioned, and you must make your own determination of its suitability and completeness of your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability or fitness of any product; and nothing herein waives any of the Seller's conditions of sale.

Figure 6 – FTIR Spectra







Figure 7 – DSC Curve (Yellow Bottle)



Neither Eastman nor its marketing affiliates shall be responsible for the use of this information, or of any product, method or apparatus mentioned, and you must make your own determination of its suitability and completeness of your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability or fitness of any product; and nothing herein waives any of the Seller's conditions of sale.

Figure 8 – DSC Curve (Blue Bottle)**Figure 9 – DSC Curve (Pink Bottle)**

Neither Eastman nor its marketing affiliates shall be responsible for the use of this information, or of any product, method or apparatus mentioned, and you must make your own determination of its suitability and completeness of your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability or fitness of any product; and nothing herein waives any of the Seller's conditions of sale.